


## MO-VS



## CERTIFICATES



## BASE MATERIAL



## CHARACTERISTICS

- Assessed for structural applications in non-cracked concrete, M8 to M24.
- Assessed for post-installed rebar connections  $\varnothing 8$  to  $\varnothing 20$ .
- Assessed for use in masonry.
- LEED and A+ certificates, Styrene free.
- Use for high loads, static or quasi-static.
- Working life of 50 and/or 100 years.
- Valid for dry, wet and flooded holes.
- Valid for zinc plated steel, hot-dip galvanized, stainless steel A2, A4 and HCR.
- Temperature range: from  $-40^{\circ}\text{C}$  to  $+80^{\circ}\text{C}$  (long term maximum temperature  $+50^{\circ}\text{C}$ ).

## VALID FOR




**M8-M24 Stud**

## APPLICATIONS

- Use in indoor and outdoor environments.
- Structural applications.
- Rebar and start rebar.
- Fixing roadside fencing.
- For fixing enginery, balconies, awnings, shelving units, billboards, catenaries, safety barriers, railings, handrails, etc.


## DRILL HOLE CONDITION



## APPLICATION EXAMPLES












## MAXIMUM LOAD RECOMMENDED [kg]



**1. RANGE**




ITEM	CODE	SIZE	PHOTO	COMOPONENT	MATERIAL	
1	<b>MOVS300</b> <b>MOVS410</b>	300 ml. 410 ml.		STYRENE FREE VNINYLESTER MORTAR	Styrene free vinyl ester resin Format: cartridges of 300 and 410 ml	12

**2. ACCESSORIES**



ITEM	CODE	PHOTO	COMPONENT	MATERIAL
1	<b>MOPISSI</b>		APPLICATION GUNS	Gun for 300 ml standard cartridges
	<b>MOPISTO</b>			Gun for 410 ml coaxial cartridges
2	<b>EQ-AC</b> <b>EQ-8.8</b> <b>EQ-A2</b> <b>EQ-A4</b>		STUD BOLTS	Threaded steel stud, class 5.8 ISO 898-1 Threaded steel stud, class 8.8 ISO 898-1 Threaded stainless steel stud A2-70 Threaded stainless steel stud A4-70
3	<b>MORCEPKIT</b>		CLEANING BRUSHES	3 Cleaning brushes kit of ø14, ø20 and ø29 mm.
4	<b>MOBOMBA</b>		CLEANING PUMP	Pump for cleaning dust and drill hole fragments
5	<b>MORCANU</b>		MIXING NOZZLE	Plastic. Helix static mixer.
6	<b>MO-TN</b>		NYLON SLEEVE	Plastic. Available in white and grey
7	<b>MO-TR</b>		METAL THREADED SLEEVE	Metal threaded sleeve M8, M10, M12, zinc plated.
8	<b>MO-TM</b>		METAL SLEEVE	Metal sleeve of ø12, ø16 and ø22,


### 3. INSTALLATION DATA

#### 3.1. CONCRETE FIXING (SET UP PARAMETERS)

SIZE		M8	M10	M12	M16	M20	M24
$d_0$ : nominal diameter	[mm]	10	12	14	18	22	26
$d_f$ : fixture hole diameter $\leq$	[mm]	9	12	14	18	22	26
$T_{ins}$ : torque $\leq$	[Nm]	10	20	40	80	150	200
Circular cleaning brush diameter		$\varnothing 14$		$\varnothing 20$		$\varnothing 29$	
<b><math>h_{ef,min} = 8d</math></b>							
$h_1$ : drill hole depth	[mm]	64	80	96	128	160	192
$s_{cr,N}$ : critical spacing	[mm]	192	240	288	384	480	576
$c_{cr,N}$ : critical edge distance	[mm]	96	120	144	192	240	288
$c_{min}$ : minimum distance to edge	[mm]	35	40	50	65	80	96
$s_{min}$ : minimum spacing	[mm]	35	40	50	65	80	96
$h_{min}$ : minimum concrete thickness	[mm]	100	110	126	158	204	244
<b>Standard Stud</b>							
$h_1$ : drill hole depth	[mm]	80	90	110	128	170	210
$s_{cr,N}$ : critical spacing	[mm]	240	270	330	384	510	630
$c_{cr,N}$ : critical edge distance	[mm]	120	135	165	192	255	315
$c_{min}$ : minimum distance to edge	[mm]	43	45	56	65	85	105
$s_{min}$ : minimum spacing	[mm]	43	45	56	65	85	105
$h_{min}$ : minimum concrete thickness	[mm]	110	120	140	158	214	262
<b><math>h_{ef,max} = 12d</math></b>							
$h_1$ : drill hole depth	[mm]	96	120	144	192	240	288
$s_{cr,N}$ : critical spacing	[mm]	288	360	432	576	720	864
$c_{cr,N}$ : critical edge distance	[mm]	144	180	216	288	360	432
$c_{min}$ : minimum distance to edge	[mm]	50	60	70	95	120	145
$s_{min}$ : minimum spacing	[mm]	50	60	70	95	120	145
$h_{min}$ : minimum concrete thickness	[mm]	126	150	174	222	284	340
 <p>5.8 / 8.8 Zinc plated stud code</p>		EQAC08110 EQ8808110	EQAC10130 EQ8810130	EQAC12160 EQ8812160	EQAC16190 EQ8816190	EQAC20260 EQ8820260	EQAC24300 EQ8824300
 <p>A2 / A4 Stainless steel stud code</p>		EQA208110 EQA408110	EQA210130 EQA410130	EQA212160 EQA412160	EQA216190 EQA416190	EQA220260 EQA420260	EQA224300 EQA424300
		<ul style="list-style-type: none"> <li><math>h_{ef}</math> depth value may be selected by the user ranging between <math>h_{ef,min} = 8d</math> and <math>h_{ef,max} = 12d</math>. Any intermediate values may be interpolated.</li> <li>Critical distances are those where anchors in a group of anchors are not influenced by one another with regard to tension load effects. For smaller distances, down to minimum distances, corresponding reduction coefficients must be applied.</li> <li>Standard studs are available for each measurement, as shown in the table.</li> </ul>					








**3.2. FIXING IN SOLID OR HOLLOW MASONRY (SET UP PARAMETERS)**

SIZE		M8	M10	M12			
Nylon Sleeve	ls	85	85	85			
	d <sub>0</sub>	15	15	20			
Mortar volume per sleeve	[ml]	15	15	27			
h <sub>1</sub> : drill hole depth ≥	[mm]	90	90	90			
h <sub>nom</sub> : sleeve installation depth	[mm]	85	85	85			
h <sub>ref</sub> : stud bolt depth ≥	[mm]	80	80	80			
t <sub>fix</sub> : thickness of material to be fixed ≤	[mm]	22	25	18			
h <sub>c</sub> : base material thickness ≥	[mm]	110	110	110			
d <sub>r</sub> : metal sheet diameter ≤	[mm]	9	12	14			
T <sub>ins</sub> : torque ≤	[Nm]	2	2	2			
Circular brush	[mm]	ø20					
Stud code		MOES08110	MOES10115	MOES12110			
Sleeve code		MOTN15085	MOTN15085	MOTN20085			
BASE MATERIAL	NYLON SLEEVE						
	M8 / M10			M12			
Critical/Minimum spacing and distance to edge		C <sub>cr</sub> = C <sub>min</sub>	S <sub>cr II</sub> = S <sub>min II</sub>	S <sub>min ⊥</sub> = C <sub>min ⊥</sub>	C <sub>cr</sub> = C <sub>min</sub>	S <sub>cr II</sub> = S <sub>min II</sub>	S <sub>min ⊥</sub> = C <sub>min ⊥</sub>
Brick number 1	[mm]	100	235	115	120	235	115
Brick number 2	[mm]	100	370	238	120	370	238
Brick number 3	[mm]	128	255	255	128	255	255
Brick number 4	[mm]	100	373	238	120	373	238
Brick number 5	[mm]	100	250	240	120	250	240
Brick number 6	[mm]	128	255	255	128	255	255
Brick number 7	[mm]	100	245	110	120	245	110




In order to make fixations in hollow bricks a nylon sleeve should be used to prevent the resin from falling through the inner holes.

BRICK TYPES

	<p><b>Brick nº 1</b>  <b>Hollow baked clay brick HLz 12-1, 0-2DF according to EN 771-1</b>  <b>Length / width / height: 235 mm / 112 mm / 115 mm</b>  <b>fb <math>\geq 12</math> N/ mm<sup>2</sup> / <math>\rho \geq 1,0</math> kg/dm<sup>3</sup></b></p>
	<p><b>Brick nº 2</b>  <b>Concrete block Hbn 4-12DF according to EN 771-3</b>  <b>Length / width / height:</b>  <b>370 mm / 240 mm / 238 mm</b>  <b>fb <math>\geq 4</math> N/ mm<sup>2</sup> / <math>\rho \geq 1,2</math> kg/ dm<sup>3</sup></b></p>
	<p><b>Brick nº 3</b>  <b>Solid baked clay brick Mz 12-2, 0-NF according to EN 771-1. Length / width / height:</b>  <b>240 mm / 116 mm / 71 mm</b>  <b>fb <math>\geq 12</math> N/ mm<sup>2</sup> / <math>\rho \geq 2,0</math> kg/ dm<sup>3</sup></b></p>
	<p><b>Brick nº 4</b>  <b>Hollow clay brick Porotherm P+W according to EN 771-1</b>  <b>length/width/height = 373 mm/250 mm/238 mm</b>  <b>fb <math>\geq 12</math> N/ mm<sup>2</sup> / <math>\rho \geq 0,9</math> kg/ dm<sup>3</sup></b></p>
	<p><b>Brick nº 5</b>  <b>Hollow baked clay brick HLzW 6-0,7-8DF according to EN 771-1</b>  <b>Length / width / height:</b>  <b>250 mm / 240 mm / 240 mm</b>  <b>fb <math>\geq 6</math> N/ mm<sup>2</sup> / <math>\rho \geq 0,8</math> kg/ dm<sup>3</sup></b></p>
	<p><b>Brick nº 6</b>  <b>Solid sillico calcareous brick KS 12-2, 0-NF according to EN 771-2. Length / width / height:</b>  <b>240 mm / 115 mm / 70 mm</b>  <b>fb <math>\geq 12</math> N/ mm<sup>2</sup> / <math>\rho \geq 2,0</math> kg/ dm<sup>3</sup></b></p>
	<p><b>Brick nº 7</b>  <b>Hollow clay brick Hueco Doble according to EN 771-1</b>  <b>length/width/height:</b>  <b>245 mm/110 mm/88 mm</b>  <b>fb <math>\geq 2,5</math> N/mm<sup>2</sup> / <math>\rho \geq 0,74</math> kg/ dm<sup>3</sup></b></p>

## 4. PRODUCT SET UP

### 4.1. CONCRETE SET UP



#### 1. DRILL

Check the concrete base is compact and porosity is insignificant.  
 Suitable for wet, dry or flooded drill holes.  
 Cartridge installation temperature:  $\geq 5\text{ }^{\circ}\text{C}$ .  
 Base material installation temperature: MO-VS  $\geq +5\text{ }^{\circ}\text{C}$   
 Use drill in hammer mode.  
 Drill to the specified diameter and depth values

#### 2 - 6. BLOW AND CLEAN

Clear the drill holes completely of dust and fragments by following the procedure shown in the picture. If the drill hole is flooded, the water must be removed before mortar is injected.

#### A - B\* - C. OPEN CARTRIDGE

Screw the nozzle into the cartridge and place the assembly in the application gun. Squeeze on the trigger repeatedly until the mortar comes out of the nozzle in a uniform grey color. Any iridescence indicates improper mixing. Always discard the first two doses of each cartridge: these are never to be used for fixing. **\*For 300 ml cartridges, cut end of bag, behind seal clip.**

#### 7. INJECT MORTAR

Insert the nozzle to the bottom of the drill hole and apply mortar: gradually remove the nozzle, ensuring there are no air bubbles. Fill the hole to  $\frac{1}{2}$  and  $\frac{3}{4}$  of its depth.  
 In the event of not fully using the cartridge, leave nozzle attached. Only change if using again and handling time has expired, remembering to discard the first two doses of mortar.

#### 8. INSTALLATION

Introduce the stud to be installed by screwing it lightly down to the installation depth value manually; ensuring the mortar covers the stud thread. The introduction of the anchor must take place within the handling time. The mortar must seep from the top of the drill hole to ensure it is completely full and there are no gaps between the stud and the drill hole.


### TEMPERATURE AND CURING TIME

TYPE	Base material temperature [ $^{\circ}\text{C}$ ]	Handling time [min]	Curing time [min]
MO-VS	min +5	18	145
	+5 to +10	10	145
	+10 to +20	6	85
	+20 to +25	5	50
	+25 to +30	4	40
	+30	4	35

#### 9. APPLY TORQUE

Once the curing time has elapsed, apply torque, never exceeding the values indicated in the table.

4.2. MASONRY SET UP



**1. DRILL**

Check the concrete base is compact and porosity is insignificant.  
 Suitable for wet, dry or flooded drill holes.  
 Cartridge installation temperature:  $\geq 5\text{ }^{\circ}\text{C}$ .  
 Base material installation temperature: MO-VS  $\geq +5\text{ }^{\circ}\text{C}$   
 Use drill in rotation mode.  
 Drill to the specified diameter and depth values

**2 - 3. BLOW AND CLEAN**

Clear the drill holes completely of dust and fragments by following the procedure shown in the picture. If the drill hole is flooded, the water must be removed before mortar is injected.

**4. POSITION SLEEVE(s)**

Insert the metal or plastic sleeve into the drill hole so it is level with the surface of the base material.

**A – B\* – C. OPEN CARTRIDGE**

Screw the nozzle into the cartridge and place the assembly in the application gun. Squeeze on the trigger repeatedly until the mortar comes out of the nozzle in a uniform grey color. Any iridescence indicates improper mixing. Always discard the first two doses of each cartridge: these are never to be used for fixing. \*For 300 ml cartridges, cut end of bag, behind seal clip.

**5. INJECT MORTAR**

Insert the nozzle to the bottom of the drill hole and apply mortar: gradually remove the nozzle, ensuring there are no air bubbles. Fill the sleeve fully.  
 In the event of not fully using the cartridge, leave nozzle attached. Only change if using again and handling time has expired, remembering to discard the first two doses of mortar.

**6. INSTALLATION**

Introduce the stud to be installed by screwing it lightly down to the installation depth value manually; ensuring the mortar covers the stud thread. The introduction of the anchor must take place within the handling time. The mortar must seep from the top of the sleeve hole to ensure it is completely full and there are no gaps between the stud and the drill hole.

**TEMPERATURE AND CURING TIME °**

TYPE	TYPE	Handling time [min]	Curing time [min]
MO-VS	min +5	18	145
	+5 to +10	10	145
	+10 to +20	6	85
	+20 to +25	5	50
	+25 to +30	4	40
	+30	4	35

**7. APPLY TORQUE**

Once the curing time has elapsed, apply torque, never exceeding the values indicated in the table.

## 5. STORAGE CONDITIONS

Keep the product stored in a cool, dry place, away from direct sunlight and heat sources, at an average temperature between +5 °C and +25 °C.



Shelf life of unopened cartridge: 18 months from the date of manufacture. The expiration date is indicated on the cartridge.

## 6. RESISTANCES

### 6.1 CONCRETE FIXATION

Characteristic resistances for C20/25 concrete for an isolated anchor (without considering anchor-to-anchor or anchor-to-edge distance effects) and class 5.8 studs or A4-70 stainless steel are shown in tables below.

#### CHARACTERISTIC RESISTANCES

CONCRETE CLASS	SIZE				M8	M10	M12	M16	M20	M24	
NON-CRACKED CONCRETE	ZINC PLATED	Tension	$h_{ef,min} = 8d$	$N_{Rk}$	[kN]	16,0	20,1	32,5	61,1	85,4	144,4
			Standard stud	$N_{Rk}$	[kN]	20,1	22,6	37,3	61,1	90,7	145,8
			$h_{ef,max} = 12d - 5.8$	$N_{Rk}$	[kN]	<u>18,0</u>	30,1	48,8	91,6	128,1	<u>177,0</u>
			$h_{ef,max} = 12d - 8.8$	$N_{Rk}$	[kN]	24,1	30,1	48,8	91,6	128,1	216,6
		Shear	All depths 5.8	$V_{Rk}$	[kN]	<u>9,0</u>	<u>15,0</u>	<u>21,0</u>	<u>39,0</u>	<u>61,0</u>	<u>88,0</u>
			All depths 8.8	$V_{Rk}$	[kN]	<u>15,0</u>	<u>23,0</u>	<u>34,0</u>	<u>63,0</u>	<u>98,0</u>	<u>141,0</u>
	STAINLESS STEEL	Tension	$h_{ef,min} = 8d$	$N_{Rk}$	[kN]	16,0	20,1	32,5	61,1	85,4	144,4
			Standard stud	$N_{Rk}$	[kN]	20,1	22,6	37,3	61,1	90,7	145,8
			$h_{ef,max} = 12d$	$N_{Rk}$	[kN]	24,1	30,1	48,8	91,6	128,1	216,6
		Shear	All depths	$V_{Rk}$	[kN]	<u>13,0</u>	<u>20,0</u>	<u>30,0</u>	<u>55,0</u>	<u>86,0</u>	<u>124,0</u>



DESIGN RESISTANCES											
CONCRETE CLASS	SIZE					M8	M10	M12	M16	M20	M24
	NON-CRACKED CONCRETE	ZINC PLATED	Tension	$h_{ef,min} = 8d$	$N_{Rd}$	[kN]	8,9	11,1	18,1	33,9	47,4
Standard stud				$N_{Rd}$	[kN]	11,1	12,5	20,7	33,9	50,4	81,0
$h_{ef,max} = 12d - 5.8$				$N_{Rd}$	[kN]	<u>12,0</u>	16,7	27,1	50,9	71,2	<u>118,0</u>
$h_{ef,max} = 12d - 8.8$				$N_{Rd}$	[kN]	13,4	16,7	27,1	50,9	71,2	120,3
Shear			All depths 5.8	$V_{Rd}$	[kN]	<u>7,2</u>	<u>12,0</u>	<u>16,8</u>	<u>31,2</u>	<u>48,8</u>	<u>70,4</u>
			All depths 8.8	$V_{Rd}$	[kN]	<u>12,0</u>	<u>18,4</u>	<u>27,2</u>	<u>50,4</u>	<u>78,4</u>	<u>112,8</u>
STAINLESS STEEL		Tension	$h_{ef,min} = 8d$	$N_{Rd}$	[kN]	8,9	11,1	18,1	33,9	47,4	80,2
			Standard stud	$N_{Rd}$	[kN]	11,1	12,5	20,7	33,9	50,4	81,0
			$h_{ef,max} = 12d$	$N_{Rd}$	[kN]	13.4	16,7	27,1	50,9	71,2	120,3
		Shear	All depths	$V_{Rd}$	[kN]	8,3	12,8	19,2	35,2	55,1	79,4

MAXIMUM LOADS RECOMMENDED (when $\gamma_F = 1.4$ )											
CONCRETE CLASS	SIZE					M8	M10	M12	M16	M20	M24
	NON-CRACKED CONCRETE	ZINC PLATED	Tension	$h_{ef,min} = 8d$	$N_{rec}$	[kN]	6,3	7,9	12,9	24,2	33,9
Standard stud				$N_{rec}$	[kN]	7,9	8,9	14,8	24,2	36,0	57,8
$h_{ef,max} = 12d - 5.8$				$N_{rec}$	[kN]	<u>8,5</u>	11,9	19,3	36,3	50,8	<u>84,2</u>
$h_{ef,max} = 12d - 8.8$				$N_{rec}$	[kN]	9,5	11,9	19,3	36,3	50,8	85,9
Shear			All depths 5.8	$V_{rec}$	[kN]	<u>5,1</u>	<u>8,5</u>	<u>12,0</u>	<u>22,2</u>	<u>34,8</u>	<u>50,2</u>
			All depths 8.8	$V_{rec}$	[kN]	<u>8,5</u>	<u>13,1</u>	<u>19,4</u>	<u>36,0</u>	<u>56,0</u>	<u>80,5</u>
STAINLESS STEEL		Tension	$h_{ef,min} = 8d$	$N_{rec}$	[kN]	6,3	7,9	12,9	24,2	33,9	57,3
			Standard stud	$N_{rec}$	[kN]	7,9	8,9	14,8	24,2	36,0	57,8
			$h_{ef,max} = 12d$	$N_{rec}$	[kN]	9,5	11,9	19,3	36,3	50,8	85,9
		Shear	All depths	$V_{rec}$	[kN]	<u>5,9</u>	<u>9,1</u>	<u>13,7</u>	<u>25,1</u>	<u>39,3</u>	<u>56,7</u>

1 kN  $\approx$  100 kg  
 The italic font underlined values indicate steel failure; rest indicates pull-out failure.

COEFFICIENTS FOR TENSION LOADS IN PULL-OUT FAILURE IN HIGH-RESISTANCE CONCRETE TYPES			
CONCRETE COEFFICIENT	C30/37	C40/50	C50/60
$\Psi_c$ (Non-cracked)	1,12	1,19	1,30

**6.2 MASONRY FIXATION**

Characteristic resistances in masonry for an isolated anchor (without considering anchor-to-anchor or anchor-to-edge distance effects) and class 5.8 studs or A4-70 stainless steel are shown in tables below.

**CHARACTERISTIC RESISTANCES ( $F_{Rk}$ )**

BASE MATERIAL*	THREADED RODS TENSION AND SHEAR [kN]		
	M8	M10	M12
BRICK NUMBER 1	2,0	2,0	2,0
BRICK NUMBER 2	2,0	1,5	2,5
BRICK NUMBER 3	1,5	1,5	2,5
BRICK NUMBER 4	1,2	1,2	1,2
BRICK NUMBER 5	1,2	0,9	0,9
BRICK NUMBER 6	0,75	0,75	1,2
BRICK NUMBER 7	0,75	0,5	0,5

**DESIGN RESISTANCES ( $F_{Rd}$ )**

BASE MATERIAL*	THREADED RODS TENSION AND SHEAR [kN]		
	M8	M10	M12
BRICK NUMBER 1	0,8	0,8	0,8
BRICK NUMBER 2	0,8	0,6	1,0
BRICK NUMBER 3	0,6	0,6	1,0
BRICK NUMBER 4	0,48	0,48	0,48
BRICK NUMBER 5	0,48	0,36	0,36
BRICK NUMBER 6	0,3	0,3	0,48
BRICK NUMBER 7	0,3	0,2	0,2

**MAXIMUM LOADS RECOMMENDED ( $F_{recom}$ ) [with  $\gamma_F= 1.4$ ]**

BASE MATERIAL*	THREADED RODS TENSION AND SHEAR [kN]		
	M8	M10	M12
BRICK NUMBER 1	0,57	0,57	0,57
BRICK NUMBER 2	0,57	0,43	0,71
BRICK NUMBER 3	0,43	0,43	0,71
BRICK NUMBER 4	0,34	0,34	0,34
BRICK NUMBER 5	0,34	0,26	0,26
BRICK NUMBER 6	0,21	0,21	0,34
BRICK NUMBER 7	0,21	0,14	0,14

\*Consult brick type on page 5, section 3.2

**6.3 CHEMICAL RESISTANCE**

Chemical resistance of the product for different kind of chemical environments and for a specific concentration.

Chemical Environment	Concentration	Result	Chemical Environment	Concentration	Result
Aqueous Solution Acetic Acid	10%	✓	Hexane	100%	C
Acetone	100%	NO DATA	Hydrochloric Acid	10%	✓
Aqueous Solution Aluminium Chloride	Saturated	✓		15%	✓
Aqueous Solution Aluminium Nitrate	10%	✓		25%	C
Ammonia Solution	5%	NO DATA	Hydrogen Sulphide Gas	100%	✓
Jet Fuel	100%	NO DATA	Isopropyl Alcohol	100%	NO DATA
Benzene	100%	NO DATA	Linseed Oil	100%	✓
Benzoic Acid	Saturated	✓	Lubricating Oil	100%	✓
Benzyl Alcohol	100%	NO DATA	Mineral Oil	100%	✓
Sodium Hypochlorite Solution	5 - 15%	✓	Paraffin / Kerosene (Domestic)	100%	C
Butyl Alcohol	100%	C	Phenol Aqueous Solution	1%	NO DATA
Calcium Sulphate Aqueous Solution	Saturated	✓	Phosphoric Acid	50%	✓
Carbon Monoxide	Gas	✓	Potassium Hydroxide	10% / pH13	C
Carbon Tetrachloride	100%	NO DATA	Sea Water	100%	C
Chlorine Water	Saturated	NO DATA	Styrene	100%	NO DATA
Chloro Benzene	100%	NO DATA	Sulphur Dioxide Solution	10%	✓
Citric Acid Aqueous Solution	Saturated	✓	Sulphur Dioxide (40°C)	5%	✓
Cyclohexanol	100%	✓	Sulphuric Acid	10%	✓
Diesel Fuel	100%	C		50%	✓
Diethylene Glycol	100%	✓	Turpentine	100%	C
Ethanol	95%	NO DATA	White Spirit	100%	✓
Ethanol Aqueous Solution	20%	C	Xylene	100%	NO DATA
Heptane	100%	C	<b>Contact only to a maximum of 25°C.</b>		C
<b>Resistant to 75°C with at least 80% of physical properties retained.</b>		✓	<b>Not Resistant</b>		X

## 7. OFFICIAL DOCUMENTATION

The following documents are available through our Sales Department or on our official website: [www.indexfix.com](http://www.indexfix.com):

- MOVS Safety Data Sheet.
- European Technical Assessment ETA 18/0400 for use in non-cracked concrete according to EAD 330499-00-0601 guide, option 7, for M8 to M24.
- European Technical Assessment ETA 20/0090 for the installation of post-installed rebar connections according to EAD 330087-00-0601 guide, with diameters from  $\varnothing 8$  to  $\varnothing 20$
- European Technical Assessment ETA 20/0091 for the use in masonry according to EAD 330076-00-0604 Guide
- Classified A+ according to French Regulation DEVL11044875A relative to the emission of volatile pollutants for indoor use.
- Certificate LEED\_MO-VS\_en\_rev1
- Declaration of Performance DoP MOVS
- INDEXcal anchor calculation software.
- INDEXmor cartridge calculation needs software.