

MS-PR



CE MARKING

CE
20
INDEX® - Técnicas Expansivas, S.L. C/ Segador, 13 26006 Logroño (La Rioja) SPAIN
MSPRX290
EN 15651-1:2012 F-EXT-INT-CC EN 15651-4:2012 PW-INT
DoP: MSPR - www.indexfix.com

Sealants for non-structural use in joints in buildings and pedestrian walkways - [Part 1](#):
Sealants for facade elements

Sealants for non-structural use in joints in buildings and pedestrian walkways - [Part 4](#):
Sealants for pedestrian walkways

PRODUCT DESCRIPTION

- Professional Adhesive and Sealant MS hybrid polymer based mono component suitable for expansion joints

CHARACTERISTICS

- Easy application even at low temperatures
- Resistant to UV-light resistant, and atmospheric effects it doesn't bleach
- High durability, resistant to ageing
- Eco-friendly, doesn't contain diluents, isocyanate and silicones. Chemically neutral and odorless
- It doesn't release any substance while curing, doesn't cause corrosion
- Good mechanical properties (150 kg/10 cm²), elasticity (300%) and flexibility
- Easily painted and sanded with most paints epoxy, polyurethane or acrylic based
- Excellent adhesion to different materials like concrete, bricks, Wood, PVC, glass, ceramic, varnished surfaces, aluminum, etc.
- For indoor and outdoor use
- Fast curing, shrinkage during hardening process below 1%.
- Thixotropic, does not slump in vertical joints
- Wide range of RAL colors and others
- Resistant to various chemicals
- Resistant to extreme climatic conditions, rain and snow
- Service temperature range: -40°C +90°C

APPLICATIONS

- Filling of expansion joints
- Sealing joints of silos, tanks, containers and other aluminum elements
- Product certified to be used in the food processing industry (Certificate ISEGA).
- Mounting and Sealing elements of kitchen, tables, decks and structures exposed to vibrations







APPLICATION EXAMPLES



BASE MATERIAL



1. RANGE

ITEM	CODE	SIZE	PHOTO	COLOR	MATERIAL	
1	MSPRB290	290 ml.			White Professional Adhesive and Sealant MS hybrid polymer based Format: cartridges of 290 ml	12
2	MSPRG290	290 ml.		 RAL 7030	Grey Professional Adhesive and Sealant MS hybrid polymer based Format: cartridges of 290 ml	12
3	MSPRN290	290 ml.			Black Professional Adhesive and Sealant MS hybrid polymer based Format: cartridges of 290 ml	12

2. ACCESSORIES

ITEM	CODE	PHOTO	COMPONENT	MATERIAL
1	MOPISSI		APPLICATION GUN	Application gun for silicone cartridges

3. TECHNICAL CHARACTERISTICS

3.1 MS-PR fresh adhesive

Characteristic	Criteria	Unit	Value
Appearance	[--]	[--]	Homogeneous paste
Skin formation	23°/50% relative humidity	Minutes	25 min
Curing speed/time	23°/50% relative humidity	mm / day	2 – 3
Resistance to flow	ISO 7390	mm	0
Application temperature	[--]	°C	+5 to +30


3.2 MS-PR cured adhesive

Characteristic	Standard	Unit	Value
Hardness shore A	ISO 868	[--]	35 - 40
Tensile resistance	ISO 10563	%	< 1,5
Module E 100%	ISO 8339	MPa	1,1 – 1,5
Elongation at break	ISO 8339	MPa	> 0,70
Tensile resistance	ISO 8339	%	150 – 250
Elongation at break	ISO 37	MPa	2 – 2,3
Change in volume	ISO 37	%	200 – 300
Service temperature	[--]	°C	-40 to +90

4. STORAGE CONDITIONS

Keep the product stored in a dry place, away from direct sunlight and heat sources, at an average temperature between +5 °C and +25 °C.

Shelf life of unopened cartridge: 15 months from the date of manufacture. The expiration date is indicated on the cartridge.



5. PRODUCT APPLICATION

Application procedure

1. The surface of the joint must be dry, hard, clean, dust and fat free. Remove all separated and badly attached pieces.
2. In case of better look is needed tape the edges with a proper masking tape.
3. Cut the cartridge at the top and screw on the nozzle, which has to be cut according to the width of the joint and placed in the gun. (see table). Apply the adhesive in line or in spots
4. During work interruption release the handle on the gun and pull the piston back. The sealant should be applied as evenly as possible.
5. At the end, use a smoothing tool, a smoothing agent soaped finger to level the sealant before the skin starts to form. It is very important to press the sealant well against the surface to be sealed. In case of gluing heavy elements, it is recommended to use supplementary fixing until the product has cured
6. Remove the masking tape before the sealant starts to harden. Fresh adhesive can be cleaned with a proper cleaner, hardened sealant should be removed mechanically.

Cartridge utilization

For optimal elasticity of a sealant the correct ratio width: depth is of extreme importance. The ratio is 2:1, 1:1 maximum. Sealant should not adhere to the bottom of the joint gap but only to its sides. The minimum and maximum joint width is 6mm and 20mm, respectively

Joint depth (mm)	Joint width (mm)					
	6	8	10	12	15	20
6	8,3	6,2	5	4,2	--	--
8	--	4,7	3,7	3,1	2,5	--
10	--	--	3,0	2,5	2,0	1,5
12	--	--	--	2,1	1,7	1,2
15	--	--	--	--	1,3	1,0
20	--	--	--	--	--	0,75

The table above shows how many linear meters of joints we can seal with one 290 ml cartridge relative to the width and depth of the joint